



TRIPLE -S CHEMICAL PRODUCTS, INC.

3464 Union Pacific Avenue
Los Angeles, CA 90023
Toll Free: 1(800) 862-5958

Tel: (323) 261-7301
Fax: (323) 261-5567

WSL-45 Clear Concrete Sealer

DESCRIPTION:

WSL-45 is a clear water born, air drying, clear lacquer, which is recommended for use on all types of concretes, bricks, marbles, etc. **WSL-45** dries to a flat/gloss, crystal clear finish providing a penetrating seal coat over concrete or brick.

ADVANTAGES:

1. Non-flammable, very safe.
2. Excellent corrosion and tarnish protection.
3. Excellent adhesion.
4. Excellent solvent resistance and humidity resistance.
5. Good to excellent stain resistance.
6. Good to excellent hardness.

Operating Conditions:

- Remove any paint, wax, dust or oil from the concrete. Rinse thoroughly with water and allow it to dry.
- **WSL-45-F** (flat) or **WSL-55-G** (gloss) is supplied "ready to go." Apply with a sponge, roller, brush or spray, using conventional air and airless spray equipment.
- Use a roller to remove excess sealer.
- A second coat should be applied two to four hours after the first coat for best results.

Safety Precautions: Avoid contact with skin, use rubber gloves when handling. Do not take internally. Keep away from children!

Packaging: Available in 1 gallon, 5 gallons pad, 55 gallons drum

The information stated herein is based on information and tests we believe to be reliable. The accuracy or completeness thereof is not guaranteed. Since conditions of use are outside our control, user shall, determine the suitability of the product for his intended use and user assumes all risk and liability.

TYPICAL PROPERTIES

Appearance:	Milky white emulsion
Total solids, by weight:	25%
pH:	8.0
Non-volatile%:	75%
Freeze/thaw stability:	Keep from freezing
Heat stability, one month, 52 °C:	O.K.
Mechanical Stability:	Excellent
Volatile organic compounds:	Less than 250
Suggested dry film thickness:	.1 mil to 2 mil

CHEMICAL RESISTANCE

.....	A	B	C
Water	10	10	10
Brake fluid	1	1	1
Transmission fluid	9	10	10
Gasoline	3	10	10
Ethanol 50%	2	10	10
Isopropanol	4	10	10
Ethylene glycol	10	10	10

A = Softness
B = Stain
C = Whitening

1 = Worse
10 = Best